



Performance Properties

VPI RUBBER FLOORING

NOTICE TO INSTALLER

THIS BROCHURE CONTAINS IMPORTANT INSTALLATION AND MAINTENANCE INFORMATION, AS WELL AS CAUTIONS AND WARNINGS. PLEASE MAKE CERTAIN THESE INSTRUCTIONS ARE PLACED IN THE HANDS OF THE FLOOR OWNER. OUR WARRANTY WILL BECOME EFFECTIVE ONLY IF THESE INSTRUCTIONS ARE FOLLOWED IN EVERY RESPECT. VPI'S EXCLUSIVE WARRANTY LIMITS VPI'S LIABILITY TO REPAIR, REPLACEMENT, OR CREDIT, AT VPI'S OPTION, ON VPI FLOOR PRODUCTS FOR WHICH A CLAIM HAS BEEN MADE ACCORDING TO VPI'S CLAIM PROCEDURE. CLAIMS FOR SURFACE DEFECTS OR VARIATIONS IN COLOR OR PATTERN MUST BE MADE TO VPI PRIOR TO INSTALLATIONS OF THE MATERIAL. FOR A COMPLETE STATEMENT OF VPI'S EXCLUSIVE WARRANTY, CONTACT: VPI CORPORATION, CUSTOMER SERVICE, P.O. BOX 451, SHEBOYGAN, WI 53082-0451.

(Decorative Slate, Decorative Hammered, Classic Raised Round & Square, Large Square, Deck Point Flooring)

GAUGES	0.125" (3.17 mm)	
SIZE	17-13/16" x 17-13/16" (452 mm x 452 mm) Micro-Squared™ (Excluding Deck Point)	35-11/16" x 35-11/16" (905 mm x 905 mm)
PROFILE & COLORS	Decorative Slate	26 colors
	Dec. Hammered	21 colors
	Classic Raised Round	16 colors
	Classic Raised Square	16 colors
	Large Square	16 colors
	Deck Point	16 colors
ASTM F-1344: Std. Specification for Rubber Floor Tile	Exceeds Requirements	
ASTM E-648 / NFPA 253: Fire Resistance	Class 1	
Critical Radiant Flux CRF (W/cm2)	<1.10	
ASTM E-662: Smoke Density	Class 1 ≤450	
ASTM E-84: Fire Resistance (Steiner Tunnel)	Class 2	
New York State Fire Prevention Code	Filed in compliance with Article 15, Part 1120	

New York City Fire Prevention Code	Accepted under section 27-348
ASTM D-3389: Abrasion Resistance (H-18 500g @ 1,000 cycles)	0.5g
ASTM D-2240: Hardness	≥85 Shore A
ASTM D-2047: Static Coefficient of Friction	0.54 (with specified conditioner) 0.67 (bare floor surface)
ASTM F-970: Static Load (modified)	1,100 psi
ASTM D-297: Density	1.72 g/cc
ASTM D-412: Tensile	1,000 psi
ASTM D-412: Elongation	170%
ASTM D-624: Tear Die	190 lb/in
ASTM F-925: Chemical Resistance	Complies (Available on request)
ASTM F-1515: Light Aging	Better than $\Delta E = 8.0$
ASTM F-1514: Heat Aging	Better than $\Delta E = 8.0$
Limited Wear Warranty	10 years



VPI Corporation, 3123 S.9th Street, PO Box 451, Sheboygan, Wisconsin 53082-0451 U.S.A.
 Phone: (920) 458-4664 – Fax: (920) 458-1368 - Customer Service: (800) 874-4240
 Email: floor@vpiflooring.com Website: www.vpiflooring.com